




YM6-15



技术检测 (Tec.)	检测标准 (TS.)	项目 (Unit.)		测试结果 (Test Result)	
耐水色牢度 (CFTW.)	AATCC107:2002 GB/T5713-1997	污染-Srain	褪色-Fading	Grade	3-3.5
		污染-Srain	褪色-Fading	等级	3-3.5
耐汗色牢度 (CFTP.)	AATCC15:2002 GB/T3922-1997	污染-Srain	褪色-Fading	Grade	3-3.5
		污染-Srain	褪色-Fading	等级	3-3.5
耐洗色牢度 (CFTW.)	ISO 105-C03:1989 GB/T3921.3-1997	污染-Srain	褪色-Fading	Grade	3-3.5
		污染-Srain	褪色-Fading	等级	3-3.5
干湿摩擦色牢度 (CFTR.)	AATCC8:2002 GB/T3920-1997	干-Dry	湿-Wet	Grade	3.5-4
		干-Dry	湿-Wet	等级	3.5-4
抗摩擦坚牢度 (Ab.Re)	ASTM D4966-98 Martindale 12Kpa			rubs	>50000转

备注:我司面料未含阻燃,阻燃需外加工.

Company Information


Contact		
☎ (Phone)	0757-23870666	23636258
☎ (Fax)	0757-23875234	23873536
✉ (E-mail)	xiaowensu@hoaubrother.com	
🌐 (Web)	www.hoaubrother.com	
📍 (Add)	顺德·龙江	精美路18号世博汇A座3-4楼(华宇总部) 亚洲国际A区一排29-32号(华宇旗舰店)

— HOAU BROTHER —



扫描二维码, 关注华宇兄弟

• 产品数据为真实检测数据 •



适用范围：休闲、沙发、民用



YM6-15

colour 18

材质：100%羊毛

克重：640g/m²

幅宽：145cm

耐磨：80000转

色牢：4级




YM6-01



YM6-02



YM6-03




YM6-16




YM6-08



YM6-09



YM6-07




YM6-06



YM6-15



YM6-14




YM6-13



YM6-10




YM6-11



YM6-12



YM6-17



YM6-18



YM6-04



YM6-05

诚信·专业·服务

● 由于拍照光线影响及显示设备的差异,导致图片与实物存在色差,请以实物为准。